

Sealing

d. temperature(25℃±5℃), humidity(60% RH)×24Hrs e.100g Scale 25℃×40 Min, Pot time is decreasing if mixture quantity increasing.

4. Properties (Temperature:25°C, Humidity:45%)

	Item	Unit	Resin	Hardener	
-	Color	_	White	Black	
-	Viscosity	Cps	THIXO	THIXO	
i, ⁻	Pot life	min	40min		
-	Tensile strength	N/mm ²	30 More than		
-	Flexural strength	N/mm ²	45 More than		
-	Compressive strength	N/mm ²	70 Moi	re than re than	
	Tensile bond strength	N/mm ²	10 Moi		
	Impact value	e Kg cm/cm ² 1.0 More t		re than	
-	Hardness	Shore D	80 More than		

JP-228A

1. Product use

- ANCHOR DOWEL or TIE BAR binder, Sealing for epoxy injection.
- 2) Sealing for various metal, stone's joint, wall and pipe hole.

2. Features

- 1) High adhesive strength with concrete, metal, glass etc.
- 2) Low shrink of curing.
- 3) Excellent mechanical strength
- 4) Outstanding THIXOTROPIC INDEX
- 5) Superior workability, soft and flexible.

3. Others

- 1) Storage requirements
- a. Store at 18~25℃ and humidity 65%
- b. Storage box should be sealed.
- c. Prohibit exposure to moisture and direct light
- d. Prohibit fire: it has risk of fire because of resin and solvent.
- 2) Shelf life
- 12 month from date of manufacture
- 3) Curing condition
- a. Mixing ratio :Resin : Hardener = 100 :100 (wt%)
- b. Degradation of physical properties if not follow
- mixing ratio.

JP-228A

987-4, GO-YEON RI, UNG-CHON MYEON, ULJU-GUN, ULSAN, KOREA